

(19)



Europäisches Patentamt

European Patent Office

Office européen des brevets



(11)

EP 0 832 171 B1

(12)

EUROPEAN PATENT SPECIFICATION

(45) Date of publication and mention
of the grant of the patent:

05.01.2000 Bulletin 2000/01

(51) Int Cl.⁷: **C10G 45/64**

(86) International application number:
PCT/EP96/02578

(21) Application number: **96921992.2**

(87) International publication number:
WO 96/41849 (27.12.1996 Gazette 1996/56)

(22) Date of filing: **12.06.1996**

(54) CATALYTIC DEWAXING PROCESS

KATALYTISCHES ENTWACHSUNGSVERFAHREN

PROCEDE CATALYTIQUE DE DEPARAFFINAGE

(84) Designated Contracting States:

AT BE CH DE DK ES FI FR GB IT LI LU NL SE

(30) Priority: **13.06.1995 EP 95401379**

(43) Date of publication of application:

01.04.1998 Bulletin 1998/14

(73) Proprietor: **SHELL INTERNATIONALE**

RESEARCH MAATSCHAPPIJ B.V.

2596 HR Den Haag (NL)

(72) Inventors:

- **GRANDVALLET, Pierre**
F-76530 Grand-Couronne (FR)
- **HUVE, Laurent, Georges**
F-76530 Grand-Couronne (FR)
- **MAESEN, Theodorus, Ludovicus, Michael**
NL-1031 CM Amsterdam (NL)

(56) References cited:

EP-A- 0 082 019	EP-A- 0 188 898
EP-A- 0 313 276	US-A- 4 088 605
US-A- 5 157 191	US-A- 5 242 676

Note: Within nine months from the publication of the mention of the grant of the European patent, any person may give notice to the European Patent Office of opposition to the European patent granted. Notice of opposition shall be filed in a written reasoned statement. It shall not be deemed to have been filed until the opposition fee has been paid. (Art. 99(1) European Patent Convention).

EP 0 832 171 B1

Description

[0001] The present invention relates to catalytic dewaxing processes.

[0002] The expression "catalytic dewaxing" is well known in the art and refers to reducing the content of waxy molecules in a hydrocarbon feedstock by contacting this feedstock with hydrogen in the presence of a suitable catalyst. The expression "waxy molecules" refers to molecules comprising a linear or slightly branched long chain aliphatic moiety, such as linear and slightly branched long chain paraffins, long chain alkylaromatics and long chain alkyl-naphthenics. Catalytic dewaxing can be attained by cracking and/or isomerisation of the waxy molecules. To that end dedicated selective cracking catalysts and dedicated selective isomerisation catalysts are available. It will be appreciated that a selective cracking catalyst mainly promotes cracking reactions, whereby also some isomerisation occurs, whilst a selective isomerisation catalyst mainly promotes isomerisation of waxy molecules, whereby also some cracking occurs. The extent wherein cracking and/or isomerisation occurs also depends on the reaction conditions applied and the type of feed used.

[0003] Several dewaxing catalysts and catalytic dewaxing processes are known in the art. For instance, in U.S. Patent No. 4,917,789 a process for the catalytic dewaxing of hydrocarbon oils is disclosed wherein the hydrocarbon oil feed is contacted with a crystalline silica polymorph silicalite catalyst at such mild dewaxing conditions that the C3 and lower hydrocarbon gas make is 2% by weight based on feed or lower. The dewaxing step may be preceded by a hydrotreatment step in order to remove sulphur from the feed or, alternatively, may be followed by a hydrotreatment step. The catalytic dewaxing process is particularly suitable for producing low pour point gas oil and diesel oil fractions. In these cases, the dewaxing step is suitably preceded by a hydrodesulphurisation step.

[0004] In European Patent Application No. 0,313,276 a catalytic dewaxing process is disclosed, wherein a waxy hydrocarbon oil is contacted with an extruded low acidity refractory oxide-bound intermediate pore size zeolite-based catalyst composition under appropriate dewaxing conditions. The catalyst may contain a hydrogenation component, such as platinum. Suitable low acidity binder materials include silica, germanium dioxide, titanium dioxide and zirconium dioxide, of which silica is the preferred binder material. The low acidity refractory oxide-bound intermediate pore size zeolite-based catalyst is shown to exhibit an improved activity and stability in catalytic dewaxing operations as compared with the same type of zeolite bound with an acidic binder such as alumina. Suitable zeolites have a pore diameter of greater than 0.5 nm and a Constraint Index of between 1 and 12 and include several ZSM-type zeolites, including ZSM-5 and ZSM-35. In the working examples the production of lube oil products having pour points of -6.7 °C and -3.9 °C was demonstrated.

[0005] In U.S. Patent No. 5,139,647 a catalytic dewaxing process for producing low pour point middle distillates (gas oil) as well as low pour point lubricating base oils is disclosed, wherein a hydrocarbon oil feed having a 90% boiling point above 316 °C (600 °F) is contacted under hydrocracking conditions with a catalyst comprising an intermediate pore size silicoaluminophosphate (SAPO) molecular sieve and a hydrogenation component. A very suitable catalyst is Pd/SAPO-11. In this dewaxing process the long-chain paraffin molecules present in the feed undergo mild cracking reactions, whilst at the same time isomerisation of n-paraffins into isoparaffins occurs. After dewaxing the effluent is separated into the middle distillate fraction and the heavier lubricating oil base stock. The latter is subsequently advantageously subjected to a hydrofinishing treatment in order to hydrogenate any olefins, diolefins and aromatics present. Such hydrofinishing step is beneficial for the stability of the final lubricating base oil.

[0006] In International Patent Application No. WO 92/01657 a catalytic dewaxing process is disclosed wherein a hydrocarbon oil feed containing straight and slightly branched paraffins having 10 or more carbon atoms is contacted under isomerisation conditions with a catalyst comprising (i) an intermediate pore size molecular sieve having a crystallite size of at most 0.5 micron, a certain acidity and isomerisation selectivity and pores with a diameter in the range of from 0.48 nm to 0.71 nm and (ii) at least one Group VIII metal, suitably platinum and/or palladium. Among the many suitable molecular sieves are listed ZSM-5, ZSM-22, ZSM-23, ZSM-35, SSZ-32, ferrierite and SAPO-11. A subsequent hydrofinishing step to increase the lube oil product's stability may be applied. In the working examples lube oil products having a pour point of -12 °C and a viscosity index of from 102 to 107 are shown to be obtainable by the process disclosed.

[0007] In International Patent Application No. WO 92/01769 a catalytic dewaxing process is disclosed wherein a waxy feed having a wax content of more than 50% by weight and/or having a pour point of above 0 °C and containing more than 70% of paraffinic carbon is contacted with a catalyst comprising a molecular sieve having oval shaped pores and at least one Group VIII metal. Suitable feedstocks include slack waxes obtained from hydrocracked or solvent refined lube oils. Suitable molecular sieves include SAPO-11, SAPO-31, SAPO-41, ZSM-22, ZSM-23 and ZSM-35. Preferred catalysts are Pt/SAPO-11 and Pt/ZSM-22. The process is stated to be suitable for the production of lube oils having pour points of below -24 °C and viscosity indices of between 125 and 180. An additional hydrofinishing step may be applied to increase the stability of the lube oil product obtained.

[0008] In U.S. Patent No. 5,149,421 a catalytic dewaxing process is described wherein a hydrocarbon oil having a boiling range above 177 °C and containing straight and slightly branched paraffins is contacted sequentially with a

layered catalyst comprising a catalyst layer containing an intermediate pore size SAPO molecular sieve and a hydrogenation component (suitably Pt-SAPO-11) and a catalyst layer containing an intermediate pore size aluminosilicate zeolite and optionally a hydrogenation component. The intermediate pore size aluminosilicate zeolite is suitably selected from the group of ZSM-22, ZSM-23 and ZSM-35, whilst platinum or palladium is used as the hydrogenation component.

[0009] In EP-A-313276 a catalytic dewaxing process is disclosed in which a waxy hydrocarbon feedstock is contacted with a silica bound ZSM-35 catalyst. The zeolite can be steamed before being used in the dewaxing process. Steaming however does not result in that the surface of the crystallite is selectively dealuminated.

[0010] In EP-A-188898 a two stage catalytic dewaxing process is disclosed in which a steamed zeolite-beta, platinum and an alumina binder comprising catalyst was used in the first step and a Ni/ZSM-5 containing catalyst in the second step. Catalysts having a silica binder are not disclosed.

[0011] Although the processes listed above perform satisfactory in many respects, there is still room for improvement. The present invention aims to provide a catalytic dewaxing process, wherein hydrocarbon oil products having greatly reduced pour points and very low cloud points can be produced at high yields thereby using a catalyst composition exhibiting an optimum combination of stability, selectivity and activity, so that it can be used for a long time without significant deactivation occurring. The present invention aims to provide such process which can be applied for dewaxing both gas oils and lubricating base oils. Furthermore, the present invention aims to provide a catalytic dewaxing process wherein the gas make can be kept at a low level and wherein the by-products formed are valuable products like naphtha and gas oil.

[0012] Accordingly, the present invention relates to processes for the catalytic dewaxing of a hydrocarbon oil feed comprising waxy molecules, which processes are defined in claims 1 and 12.

[0013] The hydrocarbon oils to be used as feed in the process according to the present invention contain waxy molecules. Minimum wax content of a hydrocarbon oil feed should be 5% by weight based on total feed, preferably at least 7.5% by weight. Concrete examples of suitable feeds, then, include waxy distillate fractions substantially boiling between 250 and 620 °C, i.e. having at least 90% by weight of their boiling range between 250 and 620 °C, which waxy distillate fractions are obtained by either atmospheric distillation or distillation under reduced pressure. Vacuum distillate fractions derived from an atmospheric residue, i.e. distillate fractions obtained by vacuum distillation of a residual fraction which in return is obtained by atmospheric distillation of a crude oil, are particularly suitable feedstocks. The boiling range of such a vacuum distillate fraction is usually for at least 90% by weight of the hydrocarbons present between 250 and 620 °C, suitably between 350 and 550 °C. An example of a suitable vacuum distillate fraction is a vacuum gas oil. Hydroprocessed waxy distillate fractions are also very suitable feedstocks and examples include hydrotreated atmospheric or vacuum gas oils and hydrocracked vacuum gas oils. Deasphalted residual oil fractions, including both deasphalted atmospheric residues and deasphalted vacuum residues, may also be applied, whilst synthetic waxy raffinates (Fischer-Tropsch waxy raffinates) and hydrocracker bottom fractions (hydrowax), i.e. those fractions having an effective cutpoint of at least 320 °C, preferably at least 360 °C, are also suitable feedstocks to be used in the process according to the present invention. Slack waxes obtained from the dewaxing of hydroprocessed or solvent refined waxy distillates may also be suitably applied as feedstocks in the process according to the present invention. In general, for lubricating base oil application, wax content of the hydrocarbon oil feed will normally be at least 10% by weight, more suitably at least 15% by weight. If lubricating base oils having viscosity indices above 120 and particularly above 135 are to be prepared, feedstocks containing relatively high amounts of waxy molecules, i.e. feeds having a wax content of at least 50% by weight, preferably at least 80% by weight and more preferably at least 90% by weight, such as the aforementioned synthetic waxy raffinates, hydrowaxes or slack waxes, are suitably used as the feedstock.

[0014] Catalytic dewaxing conditions are known in the art and typically involve operating temperatures in the range of from 200 to 500 °C, suitably from 250 to 400 °C, hydrogen pressures in the range of from 10 to 200 bar, suitably from 15 to 100 bar, more suitably from 15 to 65 bar, weight hourly space velocities (WHSV) in the range of from 0.1 to 10 kg of oil per litre of catalyst per hour (kg/l/hr), suitably from 0.2 to 5 kg/l/hr, more suitably from 0.5 to 3 kg/l/hr and hydrogen to oil ratios in the range of from 100 to 2,000 litres of hydrogen per litre of oil.

[0015] The catalyst composition to be used in the process of the present invention comprises a molecular sieve having pores with a diameter in the range of from 0.35 to 0.80 nm and containing covalently bound alumina moieties, which molecular sieve has been modified to reduce the overall mole percentage of these alumina moieties. The diameter as used in this connection refers to the maximum pore diameter. As is generally recognised, the pores in a molecular sieve are polygonal channels having a minimum and a maximum pore diameter. For the purpose of the present invention the maximum pore diameter is the critical parameter, because it determines the size of the waxy molecules which can enter the pores. The expression "alumina moiety" as used in this connection refers to an Al_2O_3 -unit which is part of the framework of the molecular sieve, i.e. which has been incorporated via covalent bindings with other oxide moieties, such as silica (SiO_2), in the framework of the molecular sieve. The mole percentage of alumina present in the molecular sieve is defined as the percentage of moles Al_2O_3 relative to the total number of moles of oxides constituting the

molecular sieve (prior to modification) or modified molecular sieve (after modification). In other words, the mole percentage of alumina is the percentage of alumina moieties relative to the total number of oxide moieties constituting the molecular sieve or modified molecular sieve.

5 **[0016]** Modification of the molecular sieve to reduce the mole percentage of alumina basically implies that the number of acid sites is reduced. This can be achieved in various ways. A first way is applying a coating of a low acidity inorganic refractory oxide onto the surface of the crystallites of the molecular sieve. Suitable inorganic oxides for this purpose are silica, zirconia or titania, of which silica is preferred. By applying such coating onto the crystallites' surface, the total number of oxide moieties in the modified molecular sieve (i.e. the original molecular sieve plus the coating) is increased, whilst the number of alumina moieties remains the same, thus resulting in a reduced mole percentage of
10 alumina. A major advantage of this method is that the number of acid sites on the surface of the crystallites of the molecular sieve is drastically reduced to essentially nil, thus allowing the waxy molecules to penetrate into the crystallites, where the desired reactions can occur, rather than initiating immediate cracking of the waxy molecules upon contact with the crystallites. The occurrence of such immediate cracking is undesired, because it causes a relatively high gas make, i.e. the formation of light gaseous hydrocarbons, which goes at the cost of the yield of both dewaxed
15 product and potentially useful by-products, such as naphtha, kero and gas oil.

[0017] Another very useful way of modifying the molecular sieve is by subjecting it to a dealumination treatment. In general, dealumination of the crystallites of a molecular sieve refers to a treatment, whereby aluminium atoms are either withdrawn from the molecular sieve framework leaving a defect or are withdrawn and replaced by other atoms, such as silicon, titanium, borium, germanium or zirconium. Dealumination can be attained by methods known in the
20 art. Useful methods are those, wherein the dealumination selectively occurs, or anyhow is claimed to occur selectively, at the surface of the crystallites of the molecular sieve. In this way, namely, the same effect as with the coated molecular sieves can be attained: the number of acid sites at the surface of the crystallites is reduced, so that the phenomenon of cracking reactions occurring as soon as the waxy molecules come into contact with the crystallites can be significantly reduced, thereby allowing the waxy molecules to enter the crystallites for the desired reactions to occur. As explained
25 hereinbefore, this is considered to positively influence the yield of both dewaxed product and useful by-products.

[0018] Modification of the molecular sieve by surface dealumination is in practice particularly used for aluminosilicate zeolites.

[0019] In U.S. Patent No. 5,157,191 a very suitable process for dealuminating the surface of an aluminosilicate zeolite is described wherein the zeolite is contacted with an aqueous solution of a hexafluorosilicate salt, most advantageously ammonium hexafluorosilicate, to extract the aluminium atoms located at the surface of the zeolite and replace
30 these atoms with silicon atoms. In said U.S. patent several hydrocarbon conversion reactions including shape-selective oligomerization of olefins to produce high viscosity lube oils, cracking, isomerization of xylene, disproportionation of toluene and alkylation of aromatics, are described in which the surface modified zeolite could be useful as a catalyst. However, no reference is made to catalytic dewaxing nor to loading the surface modified zeolite with a hydrogenation
35 component.

[0020] Another method for dealuminating the surface of zeolite crystallites is disclosed in U.S. Patent No. 5,242,676. According to this method a zeolite is contacted with a dicarboxylic acid, suitably in the form of an aqueous solution, for sufficient time to effect at least 40% reduction in surface acidity with less than 50% overall dealumination. A very suitable dicarboxylic acid is oxalic acid, whilst suitable zeolites should have a Constraint Index of greater than 1 and
40 include ZSM-5, ZSM-11, ZSM-22, ZSM-23, ZSM-35, MCM-22 and MCM-49.

[0021] Yet another method for obtaining a zeolite having a dealuminated outer surface is disclosed in U.S. patent No. 4,088,605. According to this "in situ dealumination" method a zeolite having an aluminium-free outer shell of silica is produced by a two stage method comprising (i) initiating crystallization in a crystallization medium to form the zeolite and (ii) altering the crystallization medium to substantially eliminate the aluminium therein, suitably by adding a complexing agent to the crystallization mixture which forms a complex with the aluminium ions present, after which the
45 complex formed is removed. Examples of suitable complexing agents are gluconic acid, tartaric acid and ethylenediaminetetraacetic acid (EDTA). Zeolites having an aluminium-free outer shell which can be produced in this manner include ZSM-5 and ZSM-35.

[0022] Of the (surface) dealumination methods described above, the method involving the treatment with a hexafluorosilicate, most suitably ammoniumhexafluorosilicate (AHS), has been found to offer an additional advantage. Treatment of the aluminosilicate zeolite extrudates with AHS, which extrudates are obtained by extruding the zeolite with or without binder, has been found to result in the extrudates also having an increased mechanical strength in addition to the expected dealuminated outer surface. Particularly for extrudates obtained by extruding the zeolite with a silica binder, this increase in mechanical strength occurs. The optional use of binders will be discussed in more detail
50 hereinafter.

[0023] The dealumination of the aluminosilicate zeolite results in a reduction of the number of alumina moieties present in the zeolite and hence in a reduction of the mole percentage of alumina. A very good measure for the reduction of the mole percentage of alumina is the increase of the silica to alumina ($\text{SiO}_2/\text{Al}_2\text{O}_3$) molar ratio of the zeolite as a

result of the dealumination treatment. For the purpose of the present invention, the dealumination ratio, which is defined as the ratio of $\text{SiO}_2/\text{Al}_2\text{O}_3$ molar ratio of surface dealuminated zeolite (i.e. after dealumination) to $\text{SiO}_2/\text{Al}_2\text{O}_3$ molar ratio of starting zeolite (i.e. before dealumination), is suitably in the range of from 1.1 to 3.0, preferably from 1.3 to 2.5 and even more preferably from 1.5 to 2.2. Selective dealumination of the surface of the zeolite crystallites, accordingly, also results in a reduction of the number of surface acid sites of the zeolite crystallites, whilst not affecting the internal structure of the zeolite crystallites. The extent of dealumination of the surface of the crystallites depends on the severity of the dealumination treatment. Suitably, the number of surface acid sites of the zeolite is reduced with at least 70%, preferably with at least 80% and even more preferably with at least 90%. In a most preferred embodiment the number of surface acid sites is reduced with essentially 100% by the selective dealumination, thus leaving essentially no surface acid sites at all. Without wishing to be bound by any particular theory it is believed that due to the selective dealumination of the crystallite surface the acidity of the inner part of the crystallites remains substantially unaffected and that it is this particular configuration which results in catalysts having excellent catalytic dewaxing activity, selectivity and stability.

[0024] The crystallite size of the zeolite is not particularly critical and may be as high as 100 micron. However, for an optimum catalytic activity it is preferred to employ crystallites having a size of between 0.1 and 50 micron, more preferably between 0.2 and 20 micron, whilst very good results have been obtained with crystallites having a size of between 0.5 and 5 micron.

[0025] The dewaxing catalyst composition used in the present process suitably also comprises a binder material which does not introduce acidity into the modified molecular sieve. In case of a dealuminated aluminosilicate zeolite, this implies that the binder should not re-acidify the dealuminated surface of the zeolite crystallites. Accordingly a binder should be used, which is essentially free of aluminium. A low acidity refractory oxide, which is essentially free of aluminium, is particularly suitable for this purpose. Suitable binder materials, then, include low acidity refractory oxides such as silica, zirconia, titanium dioxide, germanium dioxide, boria and mixtures of two or more of these. The most preferred binder, however, is silica. If present, the weight ratio of modified molecular sieve to binder is suitably within the range of from 10/90 to 90/10, preferably from 20/80 to 80/20 and most preferably from 50/50 to 80/20.

[0026] In addition to the modified molecular sieve and the binder material, the catalyst composition may also comprise a hydrogenation component. Particularly when used as a dewaxing catalyst in the manufacture of lubricating base oils, the presence of a hydrogenation component in the catalyst composition is advantageous. The hydrogenation component suitably comprises at least one Group VIB metal component and/or at least one Group VIII metal component. Group VIB metal components include tungsten, molybdenum and/or chromium as sulphide, oxide and/or in elemental form. If present, a Group VIB metal component is suitably present in an amount of from 1 to 35% by weight, more suitably from 5 to 30% by weight, calculated as element and based on total weight of support, i.e. modified molecular sieve plus optional binder. Group VIII metal components include those components based on both noble and non-noble metals. Particularly suitable Group VIII metal components, accordingly, are palladium, platinum, nickel and/or cobalt in sulphidic, oxidic and/or elemental form. Group VIII non-noble metals, if present at all, may be present in an amount in the range of from 1 to 25% by weight, preferably 2 to 15% by weight, calculated as element and based on total weight of support. The total amount of Group VIII noble metal will normally not exceed 10% by weight calculated as element and based on total weight of support, and preferably is in the range of from 0.1 to 5.0% by weight, more preferably from 0.2 to 3.0% by weight. If both platinum and palladium are present, the weight ratio of platinum to palladium may vary within wide limits, but suitably is in the range of from 0.05 to 10, more suitably 0.1 to 5. Catalysts comprising palladium and/or platinum as the hydrogenation component are preferred.

[0027] Molecular sieves which can be applied in the dewaxing catalyst composition must in any event meet the pore diameter requirements as given hereinbefore, i.e. they must have pores with a maximum diameter in the range of from 0.35 to 0.80 nm, preferably from 0.45 to 0.75 nm. For the purpose of the present invention it is preferred to employ aluminosilicate molecular sieves, i.e. molecular sieves of which the framework consists exclusively of silica and alumina moieties. In case the molecular sieve is modified by dealumination, it has to meet the additional requirement of being susceptible to dealumination and more particularly to selective dealumination at the surface of its crystallites. Further characteristics of the molecular sieves are determined by their desired function, i.e. selective cracking of waxy molecules, selective isomerisation of waxy molecules or a combination of both.

[0028] In one embodiment of the present invention the dewaxing catalyst is predominantly selective for cracking of waxy molecules. The word "predominantly" as used in this connection indicates that the main role of the catalyst is to promote cracking of the waxy molecules into smaller molecules, whereby some isomerisation will inevitably occur as well. Examples of suitable zeolites, then, include MFI-type zeolites having pores with diameters of 0.55 and 0.56 nm, such as ZSM-5 and silicalite, offretite having pores with diameters of approximately 0.68 nm and zeolites of the ferrierite group having pores with diameter of 0.54 nm, such as ZSM-35 and ferrierite. ZSM-23 and SSZ-32, both having a pore diameter of 0.52 nm, may also be applied. Of these, ferrierite, ZSM-5 and mixtures thereof are preferred.

[0029] In another embodiment of the present invention, the dewaxing catalyst composition is predominantly selective for isomerising waxy molecules to produce more branched molecules. Here, the word "predominantly" indicates that

the main role of the catalyst is to promote isomerisation of the waxy molecules into more branched molecules, whereby some cracking will inevitably occur as well. Examples of suitable molecular sieves are, for instance, listed in International Patent Applications Nos. 92/01657 and 92/01769, U.S. Patent No. 4,810,356 and European Patent Application No. 0,313,276 and include inter alia the aluminosilicates mordenite, zeolite beta, silicalite, ZSM-22, ZSM-23, ZSM-38, ZSM-48, ZSM-57, SSZ-24, SSZ-32, SSZ-26, SSZ-33 and MCM-22 and mixtures of two or more of these. Preferably, the molecular sieve used in a selective isomerisation catalyst is an aluminosilicate containing pores having a diameter of from 0.50 to 0.80 nm. Mordenite (0.70 nm), zeolite beta (0.55 and 0.76 nm), ZSM-23 and SSZ-32 (both 0.52 nm), are very suitable molecular sieves.

[0030] After dewaxing step (a), it may be advantageous to include a hydrofinishing step, particularly in lubricating base oil dewaxing. Such hydrofinishing step is suitably applied prior to recovery step (b), but also may be applied just after the dewaxed base oil has been recovered in step (b). Hydrofinishing is known in the art and examples of suitable hydrofinishing steps are disclosed in, for instance, U.S. Patent No. 5,139,647 and in International Patent Applications Nos. WO 92/01657 and WO 92/01769. Generally, hydrofinishing comprises contacting the hydrocarbon feed, in this case a feed comprising a dewaxed lubricating base oil, with a hydrogenation catalyst under relatively mild conditions in order to saturate at least part of the aromatics still present in the dewaxed base oil. Suitable catalysts are those normally applied for this purpose with noble metal-based catalysts, such as those comprising Pt and/or Pd supported on an amorphous silica-alumina carrier or comprising Pt on an alumina support, being preferred options. Hydrofinishing conditions normally involve operating temperatures up to 350 °C and preferably between 150 and 300 °C, operating pressures from 10 to 200 bar and weight hourly space velocities of from 0.5 to 7.5 kg/l/h.

[0031] Recovery of the dewaxed oil in step (b) of the present process can be achieved by known separation or fractionation techniques. Step (b), accordingly, normally involves separation or fractionation of the effluent from step (a), or from the optional subsequent hydrofinishing step in case of lubricating base oil dewaxing, to obtain a gaseous fraction and at least one liquid fraction as the product. Such separation or fractionation can be attained by conventional methods, such as by distillation of the effluent from the preceding step under atmospheric or reduced pressure. Of these, distillation under reduced pressure, including vacuum flashing and vacuum distillation, is most suitably applied. The cutpoint(s) of the distillate fraction(s) is/are selected such that each product distillate recovered has the desired properties for its envisaged application. Preferably, the effluent from step (a) or any hydrofinishing treatment applied subsequently is separated into a gaseous fraction and a liquid fraction which is the product. For lubricating base oils, the cutpoint will normally be at least 280 °C and will normally not exceed 400 °C, the exact cutpoint being determined by the desired product properties, such as volatility, viscosity, viscosity index and pour point. For gasoil-type feeds step (b) normally involves a gas-liquid separation comprising the removal of the gaseous products formed during the dewaxing treatment at the temperature applied, thus yielding the dewaxed gasoil as the liquid product.

[0032] In an embodiment of the present invention catalytic dewaxing of a hydrocarbon oil feed is attained by a combination of isomerisation and cracking.

[0033] In a preferred embodiment of the above process, the selective isomerisation catalyst used in step (a1) is also a catalyst composition comprising a modified molecular sieve and optionally a low acidity refractory oxide binder and/or a hydrogenation component.

[0034] Isomerisation conditions and cracking conditions applied in step (a1) and (a2), respectively, are known in the art and are similar to the catalytic dewaxing conditions described hereinbefore.

[0035] Without wishing to be bound by any particular theory it is believed that in the isomerisation step (a1) the waxy molecules present in the hydrocarbon oil feed are allowed to enter at least partially the micropores of the isomerisation catalyst. Under the isomerisation conditions applied the waxy molecules, which are able to enter the pores of the shape selective isomerisation catalyst, will be converted into isomerised molecules and to some extent lighter cracked molecules, whereas the other molecules present in the feed will remain unmodified. The linear waxy molecules, which are the least reactive molecules and which are partly responsible for the undesired cold flow properties, such as high pour points and high cloud points, will be only partially converted, so that the effluent from the hydro-isomerisation step will still contain a significant amount of linear waxy molecules. These molecules are subsequently selectively converted by contacting them with the surface deactivated selective cracking catalyst, thus leading to a significant improvement of the cold flow properties, particularly to a substantial reduction of the pour point.

[0036] Very good results can, accordingly, be obtained when the shape selective isomerisation catalyst applied in step (a1) comprises larger pores than the catalytic dewaxing catalyst applied in the subsequent selective cracking step (a2). In such configuration, namely, the mechanism described above can function in an optimum way. A very advantageous configuration comprises for instance a modified mordenite-based selective isomerisation catalyst in step (a1) and a selective cracking catalyst based on modified ZSM-5 and/or ferrierite-based in step (a2). When manufacturing lubricating base oils it is preferred to use in step (a1) a modified selective isomerisation catalyst containing a hydrogenation component. The selective cracking catalyst used in step (a2) may also comprise a hydrogenation component in that case, but the presence of such hydrogenation component has no significant impact in terms of product yield and product properties.

[0037] The above process of combined isomerisation and cracking may be conveniently carried out in a series flow mode using two separate reactors, whereby the feed is first passed through the reactor comprising a bed of shape selective hydro-isomerisation catalyst (step (a1)) and thereafter is passed through a second reactor comprising a bed of selective cracking catalyst (step (a2)). Alternatively, both steps of this process may be carried out in one single reactor using a stacked bed configuration with a bed of shape selective isomerisation catalyst on top of a bed of selective cracking catalyst. Still another option may be to apply a physical mixture of the shape selective catalyst and the selective cracking catalyst in one single catalyst bed.

[0038] As has already been described hereinbefore, after step (a2) and prior to step (b) a hydrofinishing step may be applied in case of lubricating base oil dewaxing.

[0039] The present invention also relates to a dewaxing catalyst composition comprising a hydrogenation component on a support comprising an aluminosilicate zeolite having pores with a diameter in the range of from 0.35 to 0.80 nm, which zeolite has been subjected to a dealumination treatment to reduce its mole percentage of alumina such that the ratio of the $\text{SiO}_2/\text{Al}_2\text{O}_3$ molar ratio of the zeolite after dealumination to the $\text{SiO}_2/\text{Al}_2\text{O}_3$ molar ratio of the zeolite before dealumination, is in the range of from 1.1 to 3.0. As described hereinbefore, the catalyst composition suitably also comprises a binder material which will not re-acidify the deactivated surface of the zeolite crystallites. Preferred binder materials are low acidity refractory oxides, of which silica is the most preferred option. Preferred aluminosilicate zeolites are ZSM-5, ferrierite and mixtures thereof as well as mordenite, zeolite beta, SSZ-32 and ZSM-23. The hydrogenation component present comprises at least one Group VIB metal component and/or at least one Group VIII metal component. Group VIB metal components include tungsten, molybdenum and/or chromium as sulphide, oxide and/or in elemental form. Group VIII metal components include those components based on both noble and non-noble metals. Particularly suitable Group VIII metal components, accordingly, are palladium, platinum, nickel and/or cobalt in sulphidic, oxidic and/or elemental form. Catalysts comprising palladium and/or platinum as the hydrogenation component are preferred.

[0040] The invention is further illustrated by the following examples without restricting the scope of the present invention to these specific embodiments.

[0041] In the tables given in the working examples the following abbreviations are used: ppmw refers to parts per million on a weight basis; % wt refers to percent by weight, V_{k40} and V_{k100} refer to the kinematic viscosity at 40 °C and 100 °C, respectively, and are expressed in centiStokes, cSt; VI stands for viscosity index and IBP and FBP refer to initial boiling point and final boiling point, respectively.

Example 1

[0042] A surface dealuminated ferrierite catalyst was prepared according to the following procedure. 3800 ml of a 0.11 N ammonium hexafluorosilicate solution were added to a zeolite-water slurry containing 120 grams of ferrierite ($\text{SiO}_2/\text{Al}_2\text{O}_3$ molar ratio of 11.7) and 1700 ml deionised water. The reaction mixture was heated to 100°C and maintained at this temperature for one night. The product was washed with deionised water, dried for 2 hours at 120 °C and then calcined for 2 hours at 480 °C. The surface dealuminated ferrierite thus obtained had a $\text{SiO}_2/\text{Al}_2\text{O}_3$ molar ratio of 22.3, so that the dealumination ratio was 1.9. Subsequently the surface dealuminated ferrierite was extruded with a silica binder (70% by weight of ferrierite, 30% by weight of silica binder). The extrudates were dried at 120 °C and calcined at 500 °C.

[0043] A hydrotreated heavy straight run gasoil having the properties as listed in Table I was contacted in the presence of hydrogen with the surface dealuminated, silica-bound ferrierite at a temperature of 290 °C, an outlet pressure of 55 bar, a weight hourly space velocity (WHSV) of 0.7 kg/l.hr and a gas rate of 500 NI/kg.

[0044] The results are given in Table II.

Table I

Properties of hydrotreated heavy straight run gasoil			
Density 20/4	0.860	Boiling point distribution (% wt)	
Sulphur (ppmw)	350	< 295 °C	10
Nitrogen (ppmw)	47	295 - 360 °C	40
Pour point (°C)	+6	360 - 410 °C	40
n-paraffin (%wt)	9.6	> 410 °C	10

Table II

Product characteristics			
Yield (% wt)	89.4	Gas make (% wt)	6.1
Density 20/4	0.867	Pour point (°C)	-27
Vk40 (cSt)	9.9	Cloud point (°C)	-26

[0045] From Table II it can be seen that the use of a surface dealuminated, silica-bound ferrierite as dewaxing catalyst for gasoil resulted in a pour point reduction of as much as 33 °C and a cloud point of -26 °C at low gas make and high product yield.

Example 2

[0046] A hydrocracked waxy raffinate having the properties as listed in Table III was contacted in the presence of hydrogen with the surface dealuminated, silica-bound ferrierite catalyst described in Example 1 at a temperature of 305 °C, an outlet pressure of 40 bar, a WHSV of 1.0 kg/l.hr and a gas rate of 700 NI/kg. Cutting temperature at which effluent was separated was 370 °C.

[0047] The results are given in Table IV.

[0048] Table IV shows that the surface dealuminated, silica-bound ferrierite is also very useful as a dewaxing catalyst in the manufacture of lubricating base oils. A pour point reduction of 35 °C is excellent, whilst the product yield and gas make are also very good. As can be seen, the reduction in VI due to the dewaxing has been kept limited so that the product also has a good VI.

Table III

Properties of hydrocracked waxy raffinate			
Density 70/4	0.821	Boiling point distribution (% wt)	
Vk40 (cSt)	21.6	IBP - 360 °C	10
Vk100 (cSt)	4.43	360 - 420 °C	40
VI	116	420 - 470 °C	40
Sulphur (ppmw)	< 1	470 - FBP °C	10
Nitrogen (ppmw)	< 1		
Pour point (°C)	+33	IBP (°C)	300
Wax content (%wt)	19.3	FBP (°C)	514

Table IV

Product characteristics			
Yield (% wt)	82	Gas make (% wt)	7
Vk40 (cSt)	25.1	Pour point (°C)	-2
Vk100 (cSt)	4.66	VI	101

Example 3

[0049] A surface dealuminated, silica bound ZSM-5 catalyst (70% wt surface dealuminated ZSM-5, 30% wt silica binder) was prepared in a similar way as described in Example 1 starting from a zeolite-water slurry containing 42 grams of ZSM-5 and 590 grams of deionised water. Prior to surface dealumination the ZSM-5 had a SiO₂/Al₂O₃ molar ratio of 26.0, afterwards of 51.6, which corresponds with a dealumination ratio of 2.0.

[0050] A hydrocracked waxy raffinate having the properties as listed in Table V was contacted in the presence of hydrogen with the surface dealuminated, silica-bound ZSM-5 at a temperature of 295 °C, an outlet pressure of 40 bar, a WHSV of 1.0 kg/l.hr and a gas rate of 700 NI/kg. Gaseous components were separated from the effluent by vacuum flashing at a cutting temperature of 370 °C.

[0051] The results are given in Table VI.

[0052] From Table VI it can be seen that the surface dealuminated, silica bound ZSM-5 catalyst is an excellent

dewaxing catalyst (pour point reduction of 44 °C). The product obtained, accordingly, has an excellent pour point, whilst kinematic viscosity and VI are also very good, thus making the product particularly useful as lubricating base oil. Furthermore, gas make and product yield are within commercially acceptable limits.

Table V

Properties of hydrocracked waxy raffinate			
Density 70/4	0.817	Boiling point distribution (% wt)	
Vk40 (cSt)	21.8	IBP - 380 °C	10
Vk100 (cSt)	4.51	380 - 420 °C	40
VI	121	420 - 470 °C	40
Sulphur (ppmw)	2.9	470 - FBP °C	10
Nitrogen (ppmw)	< 1		
Pour point (°C)	+27	IBP (°C)	334
Wax content (%wt)	16.7	FBP (°C)	538

Table VI

Product characteristics			
Yield (% wt)	73	Gas make (% wt)	16
Vk40 (cSt)	28.0	Pour point (°C)	-17
Vk100 (cSt)	5.01	VI	104

Example 4

[0053] The hydrocracked waxy raffinate having the characteristics as indicated in Table V was contacted in the presence of hydrogen with a catalyst comprising 0.7% by weight Pt supported on the surface dealuminated, silica-bound ZSM-5 prepared in Example 3. This catalyst was prepared by impregnating said modified silica-bound ZSM-5 with an aqueous solution of platinum tetramine hydroxide followed by drying (2 hours at 120 °C) and calcining (2 hours at 300 °C). The catalyst was activated by reduction of the platinum under a hydrogen rate of 100 l/hr at a temperature of 350 °C for 2 hours.

[0054] Process conditions were: a temperature of 282 °C, an outlet pressure of 40 bar, a WHSV of 1.0 kg/l.hr and a gas rate of 700 NI/kg.

[0055] The dewaxed lubricating base oil was recovered as the 300 °C+ fraction (i.e. cutting temperature was 300 °C). The results are indicated in Table VII.

Example 5

[0056] The same procedure as in Example 4 was repeated, only this time using a catalyst comprising 0.5% Pd supported on the surface dealuminated, silica-bound ZSM-5 prepared in Example 3 and applying an operating temperature of 290 °C. The catalyst was prepared in a similar manner as described in Example 4 only using an aqueous impregnating solution of a palladium salt. The results are indicated in Table VII.

Table VII

Product characteristics		
Property	Example 4	Example 5
Oil yield (% wt on feed)	74.4	75.5
Vk40 (cSt)	28.3	28.8
Vk100 (cSt)	5.01	5.04
VI	102	104
Pour Point (°C)	-15	-15

Table VII (continued)

Product characteristics		
Property	Example 4	Example 5
Gas make (%wt)	9.3	9.5

[0057] From Table VII it can be seen that the dewaxing performance of both catalysts is excellent (pour point reduction of 42 °C), resulting in products having a pour point as low as -15 °C. Since kinematic viscosity and VI of the product are also very good, the product is very useful as a lubricating base oil. Again, oil yield and gas make are well in line with commercial demands.

Claims

1. Process for the catalytic dewaxing of a hydrocarbon oil feed comprising waxy molecules, which process comprises the steps of:
 - (a) contacting the feed under catalytic dewaxing conditions with a catalyst composition comprising aluminosilicate zeolite crystallites having pores with a diameter in the range of from 0.35 to 0.80 nm and a low acidity refractory oxide binder material which is essentially free of alumina, wherein the surface of the aluminosilicate zeolite crystallites has been modified by subjecting the aluminosilicate zeolite crystallites to a surface dealumination treatment,
 - (b) recovering a product having a reduced pour point.
2. Process according to claim 1, wherein the ratio of the $\text{SiO}_2/\text{Al}_2\text{O}_3$ molar ratio of the zeolite after dealumination to the $\text{SiO}_2/\text{Al}_2\text{O}_3$ molar ratio of the zeolite before dealumination, is in the range of from 1.1 to 3.0.
3. Process according to claim 1 or 2, wherein the number of surface acid sites of the zeolite is reduced with at least 70%, preferably with at least 80% and even more preferably with at least 90%.
4. Process according to any one of claims 1-3, wherein the acidity of the inner part of the aluminosilicate zeolite crystallites remains substantially unaffected during the surface dealumination treatment.
5. Process according to any one of claims 1 to 4, wherein the surface dealumination treatment involves a treatment with a hexafluorosilicate, preferably ammoniumhexafluorosilicate.
6. Process according to any one of claims 1 to 5, wherein silica is the low acidity refractory oxide binder material which is essentially free of alumina.
7. Process according to any one of claims 1 to 6, wherein the catalyst composition comprises a hydrogenation component, preferably palladium and/or platinum.
8. Process according to any one of claims 1 to 7, wherein the catalyst composition is predominantly selective for cracking of waxy molecules.
9. Process according to claim 8, wherein the catalyst composition comprises ZSM-5, ferrierite or a mixture thereof as the aluminosilicate zeolite.
10. Process according to any one of claims 1 to 7, wherein the catalyst composition is predominantly selective for isomerising waxy molecules.
11. Process according to claim 10, wherein the catalyst composition comprises ZSM-23, SSZ-32 or mordenite as the aluminosilicate zeolite.
12. Process for the catalytic dewaxing of a hydrocarbon oil feed comprising waxy molecules, which process comprises the steps of:

- (a1) contacting the hydrocarbon oil feed under isomerisation conditions with a selective isomerisation catalyst composition,
 (a2) contacting the product of step (a1) under cracking conditions with a selective cracking catalyst composition as defined in claim 8 or 9, and
 5 (b) recovering a product having a reduced pour point.

13. Process according to claim 12, wherein the selective isomerisation catalyst composition used in step (a1) is a catalyst composition as defined in claim 10 or 11.
- 10 14. Process according to claim 12 or 13, wherein process steps (a1) and (a2) are carried out in a series flow mode or in a stacked bed configuration with a bed of selective isomerisation catalyst on top of a bed of selective cracking catalyst.
- 15 15. Process according to any one of claims 12 to 14, wherein the molecular sieve present in the selective isomerisation catalyst composition used in step (a1) comprises larger pores than the molecular sieve present in the selective cracking catalyst used in step (a2).
- 20 16. Process according to any one of claims 1-15, wherein the surface dealumination treatment is performed on a aluminosilicate zeolite extrudate, which extrudate is obtained by extruding the aluminosilicate zeolite crystallites with the low acidity refractory oxide binder material.

Patentansprüche

- 25 1. Verfahren zum katalytischen Entwachsen eines wachsartige Moleküle enthaltenden Kohlenwasserstofföleinsatzmaterials, welches Verfahren die folgenden Stufen umfaßt:
- (a) Inkontaktbringen des Einsatzmaterials unter katalytischen Entwachsungsbedingungen mit einer Katalysatorzusammensetzung, die Aluminosilicatezeolithkristallite mit Poren mit einem Durchmesser im Bereich von
 30 0,35 bis 0,80 nm und ein feuerfestes oxidisches Bindemittelmaterial mit niedriger Acidität, das im wesentlichen frei von Aluminiumoxid ist, umfaßt, worin die Oberfläche der Aluminosilicatezeolithkristallite durch Ausführung einer Oberflächendealuminierungsbehandlung an den Aluminosilicatezeolithkristalliten modifiziert worden ist, (b) Gewinnen eines Produktes mit einem erniedrigten Pourpoint.
- 35 2. Verfahren nach Anspruch 1, worin das Verhältnis des $\text{SiO}_2/\text{Al}_2\text{O}_3$ -Molverhältnisses des Zeoliths nach der Dealuminierung zu dem $\text{SiO}_2/\text{Al}_2\text{O}_3$ -Molverhältnis des Zeoliths vor der Dealuminierung im Bereich von 1,1 bis 3,0 liegt.
3. Verfahren nach Anspruch 1 oder 2, worin die Anzahl von sauren Oberflächenstellen des Zeoliths um wenigstens 70%, vorzugsweise um wenigstens 80% und noch mehr bevorzugt um wenigstens 90% verringert wird.
- 40 4. Verfahren nach einem der Ansprüche 1 bis 3, worin die Acidität des Innenteils der Aluminosilicatezeolithkristallite während der Oberflächendealuminierungsbehandlung im wesentlichen unbeeinträchtigt bleibt.
- 45 5. Verfahren nach einem der Ansprüche 1 bis 4, worin die Oberflächendealuminierungsbehandlung eine Behandlung mit einem Hexafluorsilicat, vorzugsweise Ammoniumhexafluorsilicat einschließt.
6. Verfahren nach einem der Ansprüche 1 bis 5, worin Siliciumoxid das feuerfeste oxidische Bindemittelmaterial mit niedriger Acidität ist, das im wesentlichen frei von Aluminiumoxid ist.
- 50 7. Verfahren nach einem der Ansprüche 1 bis 6, worin die Katalysatorzusammensetzung eine Hydrierkomponente, vorzugsweise Palladium und/oder Platin, umfaßt.
8. Verfahren nach einem der Ansprüche 1 bis 7, worin die Katalysatorzusammensetzung überwiegend für das Cracken von wachsartigen Molekülen selektiv ist.
- 55 9. Verfahren nach Anspruch 8, worin die Katalysatorzusammensetzung ZSM-5, Ferrierit oder ein Gemisch hievon als Aluminosilicatezeolith enthält.

10. Verfahren nach einem der Ansprüche 1 bis 7, worin die Katalysatorzusammensetzung überwiegend zum Isomerisieren von wachsartigen Molekülen selektiv ist.
- 5 11. Verfahren nach Anspruch 10, worin die Katalysatorzusammensetzung ZSM-23, SSZ-32 oder Mordenit als Aluminosilicatzeolith enthält.
12. Verfahren zum katalytischen Entwachsen eines wachsartige Moleküle enthaltenden Kohlenwasserstoffeinsatzmaterials, welches Verfahren die folgenden Stufen umfaßt:
 - 10 (a1) Inkontaktbringen des Kohlenwasserstoffeinsatzmaterial unter Isomerisierungsbedingungen mit einer selektiven Isomerisationskatalysatorzusammensetzung,
 - (a2) Inkontaktbringen des Produktes aus Stufe (a1) unter Crackbedingungen mit einer selektiven Crackkatalysatorzusammensetzung, wie in Anspruch 8 oder 9 definiert, und
 - 15 (b) Gewinnen eines Produktes mit einem erniedrigten Pourpoint.
13. Verfahren nach Anspruch 12, worin die in Stufe (a1) verwendete selektive Isomerisationskatalysatorzusammensetzung eine Katalysatorzusammensetzung, wie in Anspruch 10 oder 11 definiert, ist.
14. Verfahren nach Anspruch 12 oder 13, worin die Verfahrensstufen (a1) und (a2) in einem Reihenströmungsmodus oder in einer Stapelbettkonfiguration mit einem Bett aus selektivem Isomerisationskatalysator über einem Bett aus selektivem Crackkatalysator ausgeführt werden.
15. Verfahren nach einem der Ansprüche 12 bis 14, worin das Molekularsieb, das in der in Stufe (a1) verwendeten selektiven Isomerisationskatalysatorzusammensetzung vorliegt, größere Poren aufweist als das Molekularsieb, das in dem in Stufe (a2) verwendeten selektiven Crackkatalysator vorliegt.
- 25 16. Verfahren nach einem der Ansprüche 1 bis 15, worin die Oberflächendealuminierungsbehandlung an einem Aluminosilicatzeolithextrudat vorgenommen wird, welches Extrudat durch Extrudieren der Aluminosilicatzeolithkristallite mit dem feuerfesten oxidischen Bindemittelmaterial mit niedriger Acidität erhalten wird.

Revendications

- 35 1. Procédé pour le déparaffinage catalytique d'une alimentation d'huile hydrocarbonée comprenant des molécules cireuses, lequel procédé comprenant les étapes suivantes :
 - 40 (a) la mise en contact de l'alimentation sous des conditions de déparaffinage catalytique avec une composition de catalyseur comprenant des cristallites de zéolite d'aluminosilicate ayant des pores d'un diamètre dans la gamme de 0,35 à 0,80 nm et une matière formant liant d'oxyde réfractaire de faible acidité qui est essentiellement exempte d'alumine, dans lequel la surface des cristallites de zéolite d'aluminosilicate a été modifiée en soumettant les cristallites de zéolite d'aluminosilicate à un traitement de désalumination en surface, et
 - (b) la récupération d'un produit ayant un point d'écoulement réduit.
- 45 2. Procédé suivant la revendication 1, dans lequel le rapport du rapport molaire $\text{SiO}_2/\text{Al}_2\text{O}_3$ de la zéolite après désalumination au rapport molaire $\text{SiO}_2/\text{Al}_2\text{O}_3$ de la zéolite avant désalumination, se situe dans la gamme de 1,1 à 3,0.
3. Procédé suivant l'une ou l'autre des revendications 1 et 2, dans lequel le nombre de sites acides en surface de la zéolite est réduit d'au moins 70 %, avantageusement d'au moins 80 % et même plus avantageusement d'au moins 90 %.
- 50 4. Procédé suivant l'une quelconque des revendications 1 à 3, dans lequel l'acidité de la partie intérieure des cristallites de zéolite d'aluminosilicate reste sensiblement non altérée par le traitement de désalumination en surface.
- 55 5. Procédé suivant l'une quelconque des revendications 1 à 4, dans lequel le traitement de désalumination en surface implique un traitement avec un hexafluorosilicate, avantageusement de l'hexafluorosilicate d'ammonium.
6. Procédé suivant l'une quelconque des revendications 1 à 5, dans lequel de la silice est la matière formant liant d'oxyde réfractaire de faible acidité qui est essentiellement exempte d'alumine.

7. Procédé suivant l'une quelconque des revendications 1 à 6, dans lequel la composition de catalyseur comprend un composant d'hydrogénation, avantageusement du palladium et/ou du platine.
- 5 8. Procédé suivant l'une quelconque des revendications 1 à 7, dans lequel la composition de catalyseur est principalement sélective pour le craquage de molécules cireuses.
9. Procédé suivant la revendication 8, dans lequel la composition de catalyseur comprend de la ZSM-5, de la ferrièreite ou un mélange de celles-ci comme zéolite d'aluminosilicate.
- 10 10. Procédé suivant l'une quelconque des revendications 1 à 7, dans lequel la composition de catalyseur est principalement sélective pour l'isomérisation de molécules cireuses.
11. Procédé suivant la revendication 10, dans lequel la composition de catalyseur comprend de la ZSM-23, de la SSZ-32 ou de la mordénite comme zéolite d'aluminosilicate.
- 15 12. Procédé pour le déparaffinage catalytique d'une alimentation d'huile hydrocarbonée comprenant des molécules cireuses, lequel procédé comprend les étapes suivantes :
 - (a1) la mise en contact de l'alimentation d'huile hydrocarbonée sous des conditions d'isomérisation avec une composition de catalyseur d'isomérisation sélective,
 - 20 (a2) la mise en contact du produit de l'étape (a1) sous des conditions de craquage avec une composition de catalyseur de craquage sélectif telle que définie suivant l'une ou l'autre des revendications 8 et 9, et
 - (b) la récupération d'un produit ayant un point d'écoulement réduit.
- 25 13. Procédé suivant la revendication 12, dans lequel la composition de catalyseur d'isomérisation sélective utilisée dans l'étape (a1) est une composition de catalyseur telle que définie suivant l'une ou l'autre des revendications 10 et 11.
- 30 14. Procédé suivant l'une ou l'autre des revendications 12 et 13, dans lequel les étapes de traitement (a1) et (a2) sont réalisées dans un mode d'écoulement en série ou dans une configuration de lit empilée avec un lit de catalyseur d'isomérisation sélective au-dessus d'un lit de catalyseur de craquage sélectif.
- 35 15. Procédé suivant l'une quelconque des revendications 12 à 14, dans lequel le tamis moléculaire présent dans la composition de catalyseur d'isomérisation sélective utilisée dans l'étape (a1) comprend des pores plus grands que le tamis moléculaire présent dans le catalyseur de craquage sélectif utilisé dans l'étape (a2).
- 40 16. Procédé suivant l'une quelconque des revendications 1 à 15, dans lequel le traitement de désalumination en surface est réalisé sur un extrudat de zéolite d'aluminosilicate, lequel extrudat est obtenu par extrusion des cristallites de zéolite d'aluminosilicate avec la matière formant liant d'oxyde réfractaire de faible acidité.

THIS PAGE LEFT BLANK